

F.L.G. 2-0/3-1/4-2/HF-2

Synthetic lubricating greases

The benefits at a glance

- NSF-H1 registered
- Ageing and oxidation stable
- Very good water resistance
- High thermal stability



Properties

Rivolta F.L.G. lubricating greases are fully synthetic high performance lubricants for the food industry. This product range is qualified by a few numbers of fully synthetic high performance lubricating greases free from mineral oil for almost all grease lubricated applications in the area of the food industry.

F.L.G. 4-2 is the lubricant for rolling and plain bearings.

F.L.G. HF-2 is a water resistant adhesive grease for the lubrication of fittings, gear rims and gear couplings.

F.L.G. 2-0 is the right choice for centralized lubricating systems of packing machines.

F.L.G. 3-1 is offered for the use of grease lubricated gears.


Form	pasty
Colour	white (F.L.G. 2-0: beige)
odour	neutral

Fields of Application

- Open and closed gears, e.g. rolling gear (spur gear, bevel gear), helical gear, worm gear pair, bevel gear pair with pinion offset
- Gear couplings, gear rims, fittings, levers, bolts, joints, guidings metal/metal e.g. at gripper systems of food packing machines
- Rolling bearings and plain bearings, e.g. deep groove ball bearings, angular contact ball bearings, cylindrical roller bearings at chargers, bottle cleaning machines, labelling machines, bottle capping machines, filling machines, cyclones etc.

Instructions for use

Suitable application devices and accessories in our [accessories brochure](#).



Available in:

- 250 g tube (only FLG 2-0)
- 470 g cartridge (only FLG 4-2 / HF-2) (PU 12 pcs.)
- 1 kg tin (only 3-1 / 4-2 / HF-2)
- pail (10 kg and 25 kg) (only 3-1 / 4-2 / HF-2)

	Value				Norm
	F.L.G. 2-0	F.L.G. 3-1	F.L.G. 4-2	F.L.G. HF-2	
NSF Reg.-No.	128923	125884	125886	137709	–
Density at +15 °C	0,83 g/cm³	0,86 g/cm³	0,85 g/cm³		DIN 51757
Viscosity of base oil at +40 °C	100 mm²/s			280 mm²/s	DIN 51562-1
Viscosity of base oil at +100 °C	13,4 mm²/s			35,4 mm²/s	DIN 51562-1
Type of thickener	aluminium complex				–
Dropping point	–	> +200 °C			DIN ISO 2176
Worked penetration	500–540 1/10 mm	370–410 1/10 mm	265–295 1/10 mm	290–330 1/10 mm	DIN ISO 2137
NLGI-class	–	0 – 00	2	1 – 2	DIN 51818
Temperature range	-50 °C to +120 °C	-40 °C to +140 °C			–
Classification DIN	–	125884	–		DIN 51502
Classification ISO	–	L-XEBEA 00	–		ISO 6743-9
Water resistance at +90 °C/3 h	–	1			DIN 51807 T1
Oil separation at +40 °C/18 h	< 1%				DIN 51817
Corrosion protection to steel	0 – 0 Corr.-grade				DIN 51802
Corrosion effect on copper	1 Corr.-grade				DIN 51811



Bremer & Leguil GmbH

Am Burgacker 30–42 • 47051 Duisburg • Germany

Tel. +49 203 99 23-0 • Fax +49 203 2 59 01

info@bremer-leguil.de

This text contains facts and statements and is determined with our best knowledge and will be checked continuously. These statements are depending - among other reasons - on experiences gained in the industry. We only pass them on without liability. Before using our products you should test the applicability and you should convince yourself of the satisfactory performance. Our application examples and suggestions should not request to violate patent rights. Product illustrations partly consist of picture compositions and therefore, do not necessarily reflect the reality.

V250416